



CLR65

Elastocon® CLR65 is a transparent thermoplastic elastomer that has been developed for applications that require oil/plasticizer free, high strength properties and a tactile surface finish. Elastocon® CLR65 is FDA compliant and well suited for consumer goods and industrial applications requiring U.V. stability. Elastocon® CLR65 can be overmolded onto polypropylene.

Elastocon® CLR65 is supplied as ready to use pellets in 1000 lb. quantities.

Typical Physical Properties			
Property	Referenced ASTM Test Method	Test Unit	Typical Value
Hardness	ASTM D2240	Shore A	65
Specific Gravity	ASTM D792	g/cc	.89
Tensile Properties	ASTM D412		
Tensile Strength	ASTM D412	Mpa (psi)	15.2 (2205)
100% Modulus	ASTM D412	Mpa (psi)	2.05 (297)
Elongation	ASTM D412	%	838
Tear Strength	ASTM D642	pli	198

For additional technical, sales, and order assistance:

Elastocon TPE Technologies
PO Box 463
Rochester, IL 62563 USA

Sales and Technical Assistance:

Office +1 217 498 8500
Fax +1 888 231 8332
orders@etpe.com
sales@etpe.com
techsupport@etpe.com
www.etpe.com

Processing

Elastocon® thermoplastic elastomers are shear dependent and have been formulated to process on conventional thermoplastic equipment for injection molding, extrusion or blow molding.

For extrusion, a general purpose screw with a compression ratio of 2.5 to 3.0 is suggested. The feed zone temperature should be no higher than 175F. We generally suggest increasing the zone temperatures along the extruder barrel from about 300F/149C at the zone next to the feed zone, to about 350F/177C at the die body. Typical injection molding conditions for a reciprocating screw machine are listed in the chart below. These values are intended only as guidelines, and optimum conditions will vary from machine, material being modified, and mold configuration.

Suggested Processing Conditions	
Barrel Temperatures	
Rear	330-350F
Front	360-370F
Nozzle	380-400F
Mold Temperature	70F-100F
Back Pressure	100-200 psi
Injection Rate	Fast

Elastocon® CLR65 thermoplastic elastomer compound does not require drying.

Elastocon® thermoplastic elastomers are not compatible with flexible PVC and should not be blended with or used in an application where direct contact is intended.

For additional technical, sales, and order assistance:

Elastocon TPE Technologies
PO Box 463
Rochester, IL 62563 USA

Sales and Technical Assistance:

Office +1 217 498 8500
Fax +1 888 231 8332
orders@etpe.com
sales@etpe.com
techsupport@etpe.com
www.etpe.com

DISCLAIMER OF WARRANTY AND LIABILITY: Although the information and recommendations set forth herein ("Information") are believed to be correct. Elastocon, Inc., makes no representations or warranties, express or implied, as to the accuracy or completeness thereof, or of merchantability, fitness for a particular purpose, or of any other nature regarding information, or any product, process or equipment of Elastocon, Inc., or of any other manufacturer or supplier mentioned herein. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent. Elastocon, Inc. makes no representation or warranty, express or implied, that the use thereof will not infringe any patent. Persons receiving information must make their own determination as to its suitability to their purposes prior to use. In no event will Elastocon, Inc. be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the products, processes or equipment to which the Information refers.